



# RYEFLOW PLUS FLOW APPLIED ANTISLIP EPOXY FLOORING

## DESCRIPTION

Ryeflow is a medium to heavy duty epoxy resin floor finish providing an antislip, easily cleaned surface with excellent resistance to chemicals.

The smooth slightly textured finish is obtained by finishing and smoothing the surface with a specially designed Ryebrook spiked roller.

The incorporation of abrasion resistant fillers in the epoxy resin produces a floor finish with the highest order of wear resistance, combined with good antislip properties.

Three different products are available which use variable levels of fillers to enable Ryeflow to be applied at thicknesses from 2.0-6.0mm.

Ryeflow 2000	2.0-2.5mm
Ryeflow 3000	2.5-4.0mm
Ryeflow 5000	4.0-6.0mm

## Composition

3 pack solvent free epoxy resin and graded quartz aggregates.

## Appearance

Slightly textured gloss coloured finish.

## Durability

Ryeflow exhibits the highest order of abrasion resistance.

## Thickness

2.0-6.0mm

## TYPICAL INSTALLATIONS

Ryeflow is ideal for areas subject to heavy wear but requiring a slightly textured, easily cleanable surface such as storage areas, dry processing, engineering, laboratories etc.

## Substrates

Ryeflow adheres well to concrete and grano.

## Surface Preparation

To be assured of maximum adhesion and properties from Ryebrook resin products, the correct surface preparation is essential. Please refer to technical data sheet "Surface Preparation" reference TD102.

## Application Conditions

Ryeflow is a free flowing liquid which increases in viscosity as the temperature lowers. To ensure optimum finish an ambient temperature in excess of 10°C should be provided. Ideal application temperatures 25°C.

## Priming

Ryepime SF at 125g/m<sup>2</sup>. Allow to cure prior to application of Ryeflow.

## Mixing

The use of a rotary drum mixer is essential to produce a smooth even finish. Mix the resin and hardener units together thoroughly with a slow speed paddle mixer for at least 60 seconds until even coloured. Then add the Ryeflow aggregate slowly whilst mixing at the same time. Allow to mix for further 3 minutes.

## Application Technique

This product is laid in compliance with BS 8204-6 Type 5. Spread the mixed Ryeflow to required thickness using a trowel and level using a Ryebrook spiked roller.

Depending on the temperature it may be necessary to use the spiked roller after 15-30 minutes to ensure that all the air has been released.

## Coverage Rates

Ryeflow	2000	3000	5000
Nominal Thickness	2.0mm	3.0mm	5.0mm
Coverage kg/m <sup>2</sup>	3.2	5.4	9.7

Ryebrook Resins Limited

Unit 4, Kelvin Business Centre, Kelvin Way, Crawley, West Sussex RH10 9SF

Tel: 01293 565500 – Fax: 01293 565472 – Email: [sales@ryebrook.co.uk](mailto:sales@ryebrook.co.uk) – Website: [www.ryebrook.co.uk](http://www.ryebrook.co.uk)



CI/SfB: (43) Pr4  
 Issue No: 4  
 Issue Date: MAR10  
 Technical Data: D031B  
 Page Page 2 of 2

**SPECIFICATION DETAIL**

Ryepime SF to prime at 125g/m<sup>2</sup>.  
 Ryeflow at coverage rates as above.  
 Ryetech Plus at 250g/m<sup>2</sup>.

**Maintenance**

Providing contamination is not allowed to build up, regular scrubbing and mopping will maintain Ryeflow floors satisfactorily.

**Cure Schedule @ 20°C**

Pot Life (full unit)	30 minutes
Initial Set	8-10 hours
Foot Traffic	24 hours
Heavy Traffic	3-4 days
Full Chemical Resistance	7-10 days

**Chemical Resistance**

Excellent chemical resistance. Please refer to technical data sheet reference TD112.

**Grades Available**

FX, FC. Please refer to technical data sheet reference TD11.

**Colours Available**

All standard Ryebrook colours except White.

**TECHNICAL DATA**

	1000	2000	3000	5000
Compressive Strength N/mm <sup>2</sup>	36	36	37	42
Flexural Strength N/mm <sup>2</sup>	30	30	32	32
Slant Shear Bond Strength N/mm <sup>2</sup>	28	29	29	29
Density	1.6	1.65	1.9	2.0
Elastic Modulus kN/mm <sup>2</sup>	3	3	3	3
Flame Spread (BS476 Part 7)	Class 2			
Slip Resistance – Dry	85	85	85	85
- Wet	65	65	65	65
Thermal Cycle 14 days	40°C	at 100°C	@ 24	hour cycle
Showed no debonding or stress				
Ease of decontamination to BS4247: Part 1 Test A				"Excellent"

**Health and Safety**

Please read technical data sheet reference TD103 and specific health and safety data for this product provided in compliance with the requirements of EC Directive 91/155.

**Storage, Mixing & Application**

The storage, mixing and application conditions can affect the quality of the finish produced. Please read technical data sheet reference TD104.

**Technical Advice**

For further information on this or any other Ryebrook product, please contact our Technical Department on 01293 565500.