



RYEFLOW WD FLOW APPLIED EPOXY FLOORING

DESCRIPTION

Ryeflow is a medium to heavy duty water dispersed epoxy resin floor finish providing a smooth, easily cleaned surface with very good resistance to chemicals.

The smooth finish is obtained by finishing and smoothing the surface with a specially designed Ryebrook spiked roller.

The incorporation of abrasion resistant fillers in the epoxy resin produces a floor finish with the highest order of wear resistance.

Product Benefits:

Water vapour permeable: up to 400 times more permeable than standard epoxy toppings and can be used on concrete with higher residual moisture contents.

Water dispersed formulation - low odour, environmentally friendly.

Increased UV stability - less prone to UV attack than standard epoxy resin systems.

Composition

3 pack water dispersed epoxy resin and graded quartz aggregates.

Appearance

Smooth matt coloured finish.

Durability

Ryeflow WD exhibits the highest order of abrasion resistance.

Thickness

2.0mm

TYPICAL INSTALLATIONS

Ryeflow WD is ideal for areas subject to heavy wear but requiring a smooth easily cleanable surface such as storage areas, dry processing, engineering, laboratories etc.

Substrates

Ryeflow WD adheres well to concrete, screeds and grano.

Surface Preparation

To be assured of maximum adhesion and properties from Ryebrook resin products, the correct surface preparation is essential. Please refer to technical data sheet "Surface Preparation" reference TD102.

Application Conditions

Ryeflow is a free flowing liquid which increases in viscosity as the temperature lowers. To ensure optimum finish an ambient temperature in excess of 10°C should be provided. Ideal application temperatures 25°C.

Priming

Ryepime SF at 125g/m². Allow to cure prior to application of Ryeflow.

Mixing

The use of a rotary drum mixer is essential to produce a smooth even finish. Mix the resin and hardener units together thoroughly with a slow speed paddle mixer for at least 60 seconds until even coloured. Then add the Ryeflow aggregate slowly whilst mixing at the same time. Allow to mix for further 3 minutes.



CI/SfB: (43) Pr4
Issue No: 4
Issue Date: MAR10
Technical Data: TD031a
Page Page 2 of 2

Application Technique

This product is laid in compliance with BS 8204-6 Type 5. Spread the mixed Ryeflow to required thickness using a trowel and level using a Ryebrook spiked roller. Depending on the temperature it may be necessary to use the spiked roller after 15-30 minutes to ensure that all the air has been released.

Coverage Rates

Ryeflow	2000
Nominal Thickness	2.0mm
Coverage kg/m ²	3.6

SPECIFICATION DETAIL

Ryepime SF to prime at 125g/m².
Ryeflow at coverage rate as above.

Maintenance

Providing contamination is not allowed to build up, regular scrubbing and mopping will maintain Ryeflow floors satisfactorily. Ryeflow floors may be polished back to the original gloss in exactly the same way as vinyl or lino.

Cure Schedule @ 20°C

Pot Life (full unit)	30 minutes
Initial Set	8-10 hours
Foot Traffic	24 hours
Heavy Traffic	3-4 days
Full Chemical Resistance	7-10 days

Chemical Resistance

Excellent chemical resistance. Please refer to technical data sheet reference TD112.

Grades Available

FX, FC. Please refer to technical data sheet reference TD11.

Colours Available

All standard Ryebrook colours except White.

TECHNICAL DATA

	1000	2000	3000	5000
Compressive Strength N/mm ²	36	38	42	55
Flexural Strength N/mm ²	30	30	32	33
Slant Shear Bond Strength N/mm ²	28	29	29	29
Density	1.6	1.65	1.9	2.0
Elastic Modulus kN/mm ²	3	3	3	3
Flame Spread (BS476 Part 7)	Class 2			
Thermal Cycle 14 days	40°C at 100°C @ 24 hour cycle			
Showed no debonding or stress				
Ease of decontamination to BS4247: Part 1 Test A				"Excellent"

Health and Safety

Please read technical data sheet reference TD103 and specific health and safety data for this product provided in compliance with the requirements of EC Directive 91/155.

Storage, Mixing & Application

The storage, mixing and application conditions can affect the quality of the finish produced. Please read technical data sheet reference TD104.

Technical Advice

For further information on this or any other Ryebrook product, please contact our Technical Department on 01293 565500.